



CONTACT

Deutschland

Dr. Dietrich Müller GmbH
Hauptsitz und Werk Flexibles
Zeppelinring 18
26197 Ahlhorn
+49 4435 97 10-318
+49 4435 97 10-11
info@mueller-ahlhorn.com

USA

Dr. Dietrich Mueller GmbH - Sales office
USA
1201 N. Orange Street Suite 7160
19801 Wilmington, Delaware
United States
+1 302 4988371
+1 302 4988372
info.usa@mueller-ahlhorn.com

United Kingdom

Dr. Dietrich Mueller (UK) Ltd.
49 Greek Street
London W1D 4EG
United Kingdom
+44 20 80894197
+44 20 80894198
info.uk@mueller-ahlhorn.com

China

Dr. Dietrich Mueller GmbH.
Level 8, International Finance Center,
Tower 2, 8 Century Avenue
200120 Shanghai, Pudong
China
info.china@mueller-ahlhorn.com

ABOUT OUR COMPANY

Dr. Dietrich Müller GmbH is a global solution provider for electrical insulation materials, thermally conductive products, seals and technical films.

We advise on the selection of the right material and manufacture precision parts from flexible and rigid materials. We operate 6 sites and provide services to companies around the world.

We are ISO 9001 and ISO 14001 certified and UL listed as a repackager (E341377).

Dr. Dietrich Müller GmbH

PORON® 4701-40 Soft

PROPERTY	TEST METHOD	VALUE		
PHYSICAL				
Density, kg/m ³ (lb./ft ³)	ASTM D3574-95, Test A	240 (15)	320 (20)	480 (30)
Tolerance, %		± 10		
Thickness, mm (inches)		3.18 - 12.70 (0.125 - 0.500)	1.57 - 3.18 (0.062 - 0.125)	0.79 - 1.14 (0.031 - 0.045)
Tolerance, %		± 10	± 10	± 20
Standard Color (Code)		Black (04)		
Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min) Strain Rate Force Measured @ 25% Deflection	27 - 76 (4 - 11)	48 - 90 (7 - 13)	104 - 276 (15 - 40)
Typical kPa (psi)		41 (5)	76 (11)	173 (25)
Hardness, Durometer Shore O	ASTM D2240-97	12	17	34
Shore A		8	12	25
Compression Set, % max	ASTM D3574-95 Test D @ 23°C (73°F)	5		
	ASTM D3574-95 Test D @ 70°C (158°F)	10		
	ASTM D3574-95 Test J/Test D Autoclaved 5 hrs @ 121°C (250°F)	5		
Dimensional Stability, % max change	22 hrs @ 80°C (176°F) in a Forced-Air Oven	± 1		
Tensile Strength, Min. kPa (psi)	ASTM D3574-75 Test E	276 (40)	518 (75)	829 (120)
Tensile Elongation, % min.	ASTM D3574-75 Test E	100		
Tear Strength, Min. kN/m, (pli)	ASTM D264-91 Die C	0.5 (3)	0.9 (5)	2.1 (12)
Typical kNm, (pli)		1.6 (9)	2.1 (12)	3.0 (17)

PROPERTY	TEST METHOD	VALUE		
ELECTRICAL & THERMAL		240 (15)	320 (20)	480 (30)
Dielectric Constant, K' ("DK")	ASTM D150 @ 22°C (72°F) Relative Humidity 50% for 24 hrs	1.71		
Dielectric Strength, kV/m (volts/mil)	ASTM D149-97a	1969 (50)		
Dissipation Factor, tan D ("DF")	ASTM D150-98	0.05		
Volume Resistivity, ohm-cm (ohm-in)	ASTM D257-99	1 x 10 ¹² (3.9 x 10 ¹¹)		
Surface Resistivity, ohm/sq.	ASTM D257-99	2 x 10 ¹²		
Thermal Conductivity, W/m-K (BTU-in./hr/ft ² -F)	ASTM C518-98	0.065 (0.45)	0.080 (0.56)	0.127 (0.88)
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 ⁻⁴ in/in/°C (1.3 - 1.7 x 10 ⁻⁴ in/in/°F)		
TEMPERATURE RESISTANCE				
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)		
Recommended Intermittent Use, max.	UL JMST2 (UL50 and UL508)	121°C (250°F)		
Brittleness Temperature	ASTM D746-98	-40°C (-40°F)		
Cold Flexibility	MIL-P-12420D 1991 @ -40°C (-40°F)	Pass		
FLAMMABILITY & OUTGASSING				
Flammability, mm (inches)	UL 94HBF [†] (File E20305) (Pass ≥)	4.8 (0.188)	1.6 (0.062)	-
	FMVSS 302 (Pass ≥)	4.8 (0.188)	1.6 (0.062)	-
	CSA Comp HBF (File 188149) (Pass ≥)	4.8 (0.188)	1.6 (0.062)	-
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	Pass	Pass	-
Outgassing, Total Mass Loss (TML) %	ASTM E595-93 24 hrs @ 125°C (257°F) @ <7 x 10 ³ kPa	0.7	0.8	1.0
Outgassing, Collected Volatile Condensable Materials (CVCM) %		0.04	0.04	0.05
Outgassing, Water Vapor Regain (WVR) %		0.3	0.3	0.62

PROPERTY	TEST METHOD	VALUE		
ENVIRONMENTAL		240 (15)	320 (20)	480 (30)
Gasketing and Sealing	UL JMST2 (Consisting of UL50 & UL508) CAN/CSA-C22.2 No. 94-M91	File MH15464 File 188149		-
Moisture Absorption, High Humidity Exposure, % Weight Gain, Typical	AMS 3568-95	2	2	-
Water Absorption, Immersion Testing, % Weight Gain, Typical	ASTM D570-95	17	15	11
UV Resistance	ASTM G53-96	Good	Good	-
Ozone Resistance	GM 4486P-95	Pass	Pass	-
Corrosion Resistance	AMS 3568-91	Pass	Pass	-
Mildew/Bacteria Resistance	ASTM G21		Good	
Staining	ASTM D925		No Stain	

Notes:

‡Designed to meet UL 94 HBF based upon 2022 test criteria. As of 2023 items with nominal density $\geq 15.6\text{lb/ft}^3$ (250kg/m^3) are no longer eligible to be tested for UL 94 HBF but remain equivalent.

- - Represents testing not available at this time.
- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.

To order PORON materials, please contact our Sales Specialists at 860.928.3622 or via email at EMS_CT_cust_serv@rogerscorporation.com